

# WEICON CBC



certified by ABS | vibration-resistant | shock-resistant

WEICON CBC is suitable for the shimming and backfilling of systems difficult to align in the industrial and maritime sector. The "ABS Product Design Assessment" certified system serves as a replacement for fittings and worn metal sheets and ensures the direct contact to foundation plates. The special epoxy resin system has a low viscosity, is very flowable and self-levelling. It has a pot life of 30 minutes and cures nearly shrink-free. It provides a permanent high-static stability and has a high resistance to ageing. The epoxy resin system adheres particularly well to steel and concrete. It has a good compressive strength and is resistant to oils, fuels and many chemicals. It is vibration-resistant as well as temperature-resistant. Due to almost no cure shrinkage, machines and systems keep their specific alignment after the casting of WEICON CBC.

## Characteristics

Base	epoxy
Filler	Aluminium
Texture	flowable
Colour	grey

## Processing

Processing temperature	+15°C to +40°C	
Component temperature	>3 °C above dew point	
relative air humidity	< 85 %	
Mixing ratio by weight	100:26	
Mixing ratio by volume	100:47	
Viscosity of the mixture	at +25 °C	45.000 mPa·s
Density of the mixture	1,5 g/cm³	
Consumption	Layer thickness 1.0 mm	1,5 kg/m²
max. layer thickness	per step	30 mm

## Curing

Pot life	at 20 °C, 10 kg batch	30 min.
Additional layer after	(35 % strength)	6 h
Working strength after	(80 % strength)	10 h
Final strength	(100 % strength)	24 h
Shrinkage	0,06 %	

## Mechanical properties after curing

- measured after curing at	24 h RT + 4 h 60 °C	
Tensile strength	DIN EN ISO 527-2	35 MPa
Elongation at break (tensile)	DIN EN ISO 527-2	1,4 %
E-modulus (tensile)	DIN EN ISO 527-2	2700-3200 MPa
Compressive strength	DIN EN ISO 604	70 MPa
Impact strength	DIN EN ISO 179-1/1eU	3,7 kJ/m²
Hardness (Shore D)	DIN ISO 7619	83±3
Adhesive strength	DIN EN ISO 4624	12 MPa
Lap shear strength material thicken. 1,5mm DIN EN 1465		
Steel 1.0338 sandblasted	16 MPa	
Stainless steel V2A sandblasted	17 MPa	
Aluminium sandblasted	9 MPa	
Galvanized steel	5 MPa	

## Thermal parameters

Temperature resistance	-40°C to +160°C	
Tg after curing at room temperature (DSC)	~ +52 °C	
Tg after tempering (at 120°C) (DSC)	+77 °C	
Heat deflection resistance	DIN EN ISO 75-2	+55 °C
Thermal conductivity	DIN EN ISO 22007-4	0,5 W/m·K
Heat capacity	DIN EN ISO 22007-4	1,05 J/(g·K)

## Electrical parameters

Resistance	DIN EN 62631-3-1	4,3·10 <sup>12</sup> Ω·m
magnetic	no	

## Specific properties

IMPA Code	812955/56
ISSA Code	75.510.01

## Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

## Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

## WEICON CBC



### Surface pre-treatment

The successful application of WEICON CBC depends on the thorough preparation of the surfaces. This is the most important factor for overall success. Dust, dirt, oil, grease, rust and moisture or wetness have a negative impact on the adhesion. Therefore, before processing WEICON CBC, the following points must be observed: Foundation areas (structure element and structure foundation) need to be clean, dry and free of grease. Therefore, grease, oil, rust, loose concrete, cement milk, and paint need to be thoroughly removed. For cleaning and degreasing, we recommend WEICON Cleaner Spray S. The resin component should of the WEICON CBC should be preheated to approx. +25°C. Smooth and particularly heavily soiled surfaces should additionally be treated by mechanical surface pre-treatment, e.g. by grinding or preferably by blasting. In case of blasting, the surface should be brought to a degree of purity of SA 2 ½ - "Near White Blast Cleaning" (according to ISO 8501/1-2, NACE, SSPC, SIS). In order to achieve an optimum surface roughness of 75 - 100 µm, angular, disposable blasting media (aluminum oxide, corundum) should be used. The surface quality is negatively influenced by the use of reusable blasting media (slag, glass, quartz), but also by ice blasting. The air for blasting must be dry and oil-free. Metal parts that have come into contact with sea water or other salt solutions should first be rinsed thoroughly with demineralised water and, if possible, left to rest overnight so that all salts can be dissolved from the metal. Before each application of WEICON CBC, a test for soluble salts should be carried out according to the Bresle method (DIN EN ISO 8502-6). The maximum amount of soluble salts remaining on the substrate should not exceed 40 mg/m<sup>2</sup>. Heating and repeated blasting of the surface may be necessary to remove all soluble salts and moisture. After each mechanical pre-treatment, the surface should be cleaned again with WEICON Cleaner Spray S and protected from further contamination until the coating is applied. Areas where no adhesion to the substrate is desired must be treated with silicone-free mould release agents. For smooth surfaces, we recommend WEICON Mould Release

Agent Liquid F 1000 or, for porous surfaces, WEICON Mould Release Agent Wax P 500. After the surface pre-treatment, WEICON CBC should be applied as soon as possible (within one hour) to avoid oxidation, flash rust or new contamination.


### Formwork

Line the surfaces, which are going to be cast, with the already prepared

formwork material and prepare for casting according to the formwork plan.

#### Formwork 1

Cut the formwork material (foam material) to the required size. The front foam strip should reach the upper edge of the building component.




#### Formwork 2

Before adjusting, coat the formwork material, e.g. made of foam boards, with a release agent. When using adjustment screws for aligning the installation, they must also be coated with a release agent wax to protected from the casting resin and to ensure easy loosening of the screws after the resin has cured.

#### Note


The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

# WEICON CBC




### Formwork 3

Exposed screw holes should be covered with a flexible foam tube. Before attaching the foam tubes, they must also be covered with a release agent wax, for example WEICON Mould Release Agent Wax P 500.




### Formwork 5

After completing the formwork, small cracks, gaps and angles should be sealed with WEICON Speed-Flex. Make sure that all areas are sealed well. Additional sealing after casting CBC is very difficult, should leakages appear then. Once the formwork is completed according to the formwork plan, preparations for casting CBC can be made.



### Formwork 4

The front part of the formwork is closed with a foam board and a folded sheet metal, leaving a gap of at least 40 mm to the base plate to ensure complete ventilation. To attach the folded sheet metal, WEICON Speed-Flex is ideal.




### Mixing

Before adding the hardener, it is absolutely necessary to stir up the resin with its fillers thoroughly and bubble-free. Then the hardener can be added. Mix the components for at least four minutes thoroughly and bubble-free with mechanical mixers at a low speed of 300-1000 rpm to get a uniform mixture. Caution! Do not immerse or remove drill with Stirrer Stainless Steel in/ from resin container while switched on! This will produce air bubbles within the compound, which

Note  
The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

## WEICON CBC

will later on have a negative effect on the product's static qualities. Only prepare a batch as large as can be processed within the pot life. The specified mixing ratio by weight (max. deviation +/- 2%) must be strictly observed. CBC is available in complete processing packages with matching amounts of resin and hardener. To avoid mixing errors, a complete processing package should always be used up. The specified pot life refers to a material batch of 10kg and +20°C material temperature. Mixing larger quantities or higher processing temperatures will result in faster curing due to the typical reaction heat of epoxy resins. Portioning the total quantity increases the pot life.



### Casting

Apply the casting resin immediately, after mixing thoroughly. To prevent air bubbles, pour as close to the casting surface as possible. For curing and complete

ventilation, an ambient temperature of at

least +20°C is ideal. Air bubbles can have a negative effect on the product's static properties. Cast the cavity, until an overflow of 15 mm to 20 mm of the lower edge of the

component's foot is reached. For producing a retain sample, the screw-on lid of the hardener container can be used.

### Curing

Ideally, the application should be carried out at room temperature (+20 °C). Higher temperatures shorten the curing (rule of thumb: Each increase by +10°C (50°F) above room temperature will decrease the curing time by half) At temperatures below +16°C the pot life and cure time will slow down; below approx. +5°C no reaction will take place any more. At low ambient temperatures, make sure that the temperature is at least +15°C until the compound is fully cured. For heating the compound,

only flame-free heat sources, such as electronic hot air blowers, should be used. Cure speed at different temperatures: +15°C: 36 hours +20 °C: 24 hours +25 °C: 18 hours +30 °C: 12 hours +35 °C: 8 hours

### Sheeting

After full cure, the formwork can be removed carefully and completely. Then, bolts can be installed and nuts can be tightened with

the predefined torque value (for securing the bolts, we recommend

WEICONLOCK AN 302-72).

### Storage

Store WEICON CBC at room temperature (+20°C) in a dry place. Unopened containers can be stored at temperatures of +18°C to +28°C for at least 24 months after delivery date.

### Scope of delivery

Processing Spatula | Contour Spatula Flexy | Instructions for Use | Gloves

### Accessories

11202500	Cleaner Spray S, 500 ml, transparent
15200005	Cleaner S, 5 L, colourless, transparent
11207400	Surface Cleaner, 400 ml, transparent
15207005	Surface Cleaner, 5 L, transparent
10604025	Mould Release Agent Liquid F 1000, 250 ml, white, milky
10604515	Mould Release Agent Wax P 500, 150 g
10539115	Repair Stick Multi-Purpose, 115 g, vintage white
10850005	Glass Fibre Cloth Tape, 1 PCE, dark grey
10953001	Processing spatula, 1 PCE
10953003	Processing spatula, 1 PCE
10953010	Stirrer Stainless Steel, 1 PCE
15841500	Pump Dispenser WPS 1500, 1 L
10851020	Injection Packer Set, 1 PCE
10851021	Injection Packer/ rectangular, 1 PCE
10851022	Injection Packer/ flat, 1 PCE
13955001	Empty cartridge, 1 PCE
13250001	Cartridge Gun, 1 PCE
52000035	Cable Scissors No. 35, 1 PCE
10851010	Processing Kit, 1 PCE
13602310	Speed-Flex® MS-Polymer, 310 ml, grey

### Recommended equipment

Drilling machine Foam strip, foam pipe Sheet steel angle Angle grinder Blasting machine Heating pack, hot air blower or fan heater Fabric tape Paint brush, foam roller Lint-free cloths

### Conversion table

(°C x 1,8) + 32 = °F	Nm x 8,851 = lb·in
mm/25,4 = inch	Nm x 0,738 = lb·ft Nm
µm/25,4 = mil	x 141,62 = oz·in
N x 0,225 = lb	mPa·s = cP
N/mm <sup>2</sup> x 145 = psi	N/cm x 0,571 = lb/in
MPa x 145 = psi	kV/mm x 25,4 = V/mil

### Available sizes:

10110030	WEICON CBC, 3 kg, grey
10110110	WEICON CBC, 10 kg, grey

#### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

# WEICON CBC

	WEICON A	WEICON B	WEICON BR	WEICON C	WEICON F	WEICON F2	WEICON HB 300	WEICON SF	WEICON ST	WEICON TI	WEICON UW	WEICON WR2	WEICON HP	WEICON Ceramic BL	WEICON GL	WEICON GL-S	WEICON Ceramic W	WEICON Ceramic HC 220	WEICON WP	WEICON WR	WEICON CBC	
Repair and moulding	x	x	x	x	x	x	x	x	x	x	x	x										
Adhesive				x	x		x		x				x									
Wear protection														x	x	x	x	x	x			
Potting and gap filling	x					x						x									x	x

To the product detail page:



**Note**

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com

WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 info@weicon.com.sg

WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es

WEICON Italia S.r.L. Italy phone +39 (0) 010 2924 871 info@weicon.it

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr

# WEICON CBC

## Chemical resistance of WEICON Plastic Metals after curing\* (Excerpt)

Exhaust fumes	+	Potassium carbonate	+
Acetone	o	Potassium hydroxide 0-20 % (caustic potash)	+
Ethyl ether	+	Milk of lime	+
Ethyl alcohol	o	Carbolic acid	-
Ethylbenzene	-	Creosote oil	-
Alkalis (alkaline substances)	+	Cresylic acid	-
Hydrocarbons, aliphatic (petroleum derivatives)	+	Magnesium hydroxide	+
Formic acid >10 % (methanoic acid)	-	Maleic acid (cis-ethylenedicarboxylic acid)	+
Ammonia anhydrous 25%	+	Methanol (methyl alcohol) <85 %	-
Amyl acetate	+	Mineral oil	+
Amyl alcohol	+	Naphthalene	-
Hydrocarbons, aromatic (benzene, toluene, xylene)	+	Naphthene	-
Barium hydroxide	+	Sodium carbonate (soda)	+
Petrol (92-100 octane)	+	Sodium bicarbonate (sodium hydrogen carbonate)	+
Hydrobromic acid <10 %	+	Sodium chloride (table salt)	+
Butyl acetate	+	Sodium hydroxide >20 % (caustic soda)	o
Butyl alcohol	+	Caustic soda	+
Calcium hydroxide (slaked lime)	+	Heating oil, diesel	+
Chloroacetic acid	-	Oxalic acid <25 % (ethanedioic acid)	+
Chloroform (trichlormethane)	o	Perchloraethylene	o
Chlorosulphuric acid (wet and dry)	-	Kerosene	+
Chlorinated water (swimming pool concentration)	+	Oils, vegetable and animal	+
Hydrochloric acid	+	Phosphoric acid <5%	+
Chromium bath	+	Phthalic acid, phthalic anhydride	+
Chromic acid	+	Crude oil	+
Diesel fuels	+	Nitric acid <5%	o
Mineral oil and mineral oil products	+	Hydrochloric acid <10 %	+
Acetic acid diluted <5%	+	Sulphur dioxide (wet and dry)	+
Ethanol <85 % (ethyl alcohol)	+	Carbon disulphide	+
Greases, oils and waxes	+	Sulphuric acid <5%	o
Hydrofluoric acid diluted	o	White spirit	+
Tannic acid diluted <7%	+	Carbon tetrachloride (tetrachloromethane)	+
Glycerin (trihydroxipropane)	+	Tetralin (tetrahydronaphthalene)	o
Glycol	o	Toluene	-
Humic acid	+	Hydrogen peroxide <30 % (hydrogen superoxide)	+
Impregnating oils	+	Trichloraethylene	o
Potash	+	Xylene	-

+ = resistant 0 = for a limited time - = not resistant \*The storage of all WEICON Plastic Metal types was carried out at +20°C chemical temperature.

**Note**

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com

WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 info@weicon.com.sg

WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es

WEICON Italia S.r.l. Italy phone +39 (0) 010 2924 871 info@weicon.it

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr